

**TECHNICAL DATA SHEET***Revision date: 13.02.2023***ACRYLIC AEROSOLS**

<b>Article number:</b>	<b>26404 (clear coat), 26406 (clear coat matt)</b>
<b>Colour:</b>	Transparent
<b>Intended use:</b>	Car refinishing product/ Clear coating material, Varnish.
<b>General characteristics:</b>	High quality clear varnish for surfaces, of treated metal, aluminum, glass, stone, and various types of plastics.
<b>Product characteristics:</b>	<ul style="list-style-type: none"><li>▪ Fast drying</li><li>▪ Scratch free and shock proof</li><li>▪ Resistant to weather influences</li><li>▪ Corrosion preventive</li><li>▪ UV-resistant and non-fading</li><li>▪ Excellent adhesion</li></ul>
<b>Physical and chemical properties:</b>	
<b>Contents:</b>	500 ml
<b>Base:</b>	Acrylic resin
<b>Gloss:</b>	High gloss/Matt
<b>VOC-content:</b>	Approximately 90% w/w
<b>Solid Content:</b>	Approximately 10% w/w
<b>Coverage:</b>	1,5 to 2 m <sup>2</sup>
<b>Dust dry:</b>	After approximately 6 minutes
<b>Tack free:</b>	After 10 to 20 minutes
<b>Hardened/re-sprayable:</b>	After 2 hours
<b>Heat resistant:</b>	To 110°C

**Application process:**

Before use, carefully read the directions on the packaging and act accordingly

**Processing conditions:**

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be at least +10 °C and max. air humidity should not exceed 80%.

- **Pre Treatment:** The surface should be clean, dry and free of grease. Slightly sand the surface (grain 600).

**Treatment:** The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimeters.

Apply the clear varnish in several thin layers.

Before applying the next layer, again shake the aerosol.

**After use:** After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

This release replaces all eventually earlier issued versions.

For additional information, not contained in this technical data sheet, please contact the supplier under:

e-mail: [info@chamaeleon-produktion.de](mailto:info@chamaeleon-produktion.de)

For safety information, please refer to the corresponding safety data sheet.